

PRE-POWDERED *Latex Examination Gloves*



GLOVE ATTRIBUTES

Type	Pre-Powdered and Non-Sterile
Material	Natural Rubber Latex
Donning Powder	Bio-Absorbable USP Cornstarch
Color	Natural
Sizes	X-Small, Small, Medium, Large, X-Large
Shape	Ambidextrous
Cuff	Beaded Cuff
Surface	Smooth, Textured
Quality System	ISO 13485 : 2003 GMP
Usage	For single use only
Packaging	100 gloves per dispenser box, by weight 10 Boxes per case
Minimum Order	One full container load



CERTIFICATIONS :

- ISO 9001 : 2000
- ISO 13485 : 2003
- CE Certificate of Conformity
- US FDA K 891242
- TIS - Thai Industrial Standard
- Thai FDA
- Thailand Brand

Features & Benefits :

- Non-Sterile, suitable for medical and non-medical applications.
- Pre - Powdered with bio absorbable USP cornstarch for easier donning.
- Low modulus latex for greater comfort and natural fit.
- Excellent durability and elasticity.
- Smooth surface improves touch sensitivity.
- Textured surface allows for a secure and firm grip.

Standard of Conformance :

- ASTM D3578
- EN 455 Part 1, 2, 3
- ISO 9001 : 2000 Quality Management System



CE Cert no. AK 500450440001



Ref.No.1-1-04-17-06-00007



3100. 1056-2548



ISO 13485 : 2003 EN ISO 9001:2000
Certified by TÜV Rheinland Product Safety GmbH

Dr. Boo Co., Ltd.

DR. BOO produces Pre-Powdered and Powder-Free latex examination gloves according to ASTM D3578 and EN 455 Part 1, 2, 3 international standard requirements. All our gloves are made of premium latex that features superior properties and tactile sensitivity for an excellent fit, feel and strength.

PRE-POWDERED *Latex Examination Gloves*



The best examination gloves choice of laboratory professionals and healthcare providers.

Physical Specifications

Gloves Size		Width	Length	Long Cuff
Dimension	Extra Small	70 ± 10	≥ 220	Please contact us for custom dimension.
	Small	80 ± 10	≥ 220	
	Medium	95 ± 10	≥ 230	
	Large	111 ± 10	≥ 230	
	Extra Large	115 ± 10	≥ 230	
Thickness	Cuff (mm.)	0.08 - 2.00 min		Please contact us for custom thickness.
	Palm (mm.)	0.08 - 2.00 min		
	Finger (mm.)	0.08 - 2.00 min		
			Before Ageing	After Ageing
Physical Properties	Tensile Strength (Mpa)		min 18.0	min 14.0
	Elongation (%)		min 650	min 500
	Stress at 500% Elongation (Mpa)		max 5.5	n.a.
	Hole : Watertight (Level/AQL)		G-1/2.5	G-1/2.5
	Physical Properties & Etc. (Level/AQL)		S-2 / 4.0	S-2 / 4.0
	Physical Dimension & Etc. (Level/AQL)		S-2 / 4.0	S-2 / 4.0

Specification and products shown are correct at the time of printing and may be subjected to changes without prior notice.

CAUTION : This product contains natural rubber latex which may cause allergic reactions. Safe use of this glove by or on latex sensitized individuals has not been established.

DR. BOO Company Limited.

Plant : 662/1-4 Village 3, Tambon Kao Kan Song,
Sri Racha District, ChonBuri

Bangkok : Wall Street Tower Bldg., 11th Floor, Room 1102,
33/48 Surawong Road, Suriyawong, Bangrak,
Bangkok 10500 Thailand

Tel : (662) 267-0685-90 FAX : (662) 266-7972-3
E-Mail : marketing@drboo.co.th / drboo@drboo.co.th /
www.drboo.co.th